

impregnated contaminants. Refer to CFI Bulletin G-3 and ASTM D-4258 for suggested procedures and additional preparation guides. Follow cleaning with acid etch or sandblast.

Application

Thoroughly mix each component, then combine components and mechanically mix. **Allow to** stand for approximately 45 minutes to start initial chemical reaction before using. Surface temperature of substrate **must** be above 50°F. Apply by brush, roll, or spray (air or airless).

This primer must be topcoated within 7 days of application. Wearcoat 490 is normally topcoated with Wearcoat 480 or 491 epoxies or Wearcoat 100 urethane finishes. Refer to related technical bulletins for further information on these finishes.

Precautions

Contains aromatic hydrocarbons and glycol ethers. **HARMFUL OR FATAL IF SWALLOWED. FLAMMABLE. Vapor Harmful, Eye Irritant.** If swallowed, do not induce vomiting. Call physician immediately. Avoid prolonged contact with skin, do not breathe vapor or spray mist. In case of contact with eyes, flush repeatedly with water and contact physician.

Keep away from heat, sparks and open flames. Prohibit smoking. Use explosion proof equipment. Use with adequate ventilation. In confined areas, use adequate forced ventilation during application and drying. In areas where there is a minimum of air movement, a fresh air mask should be used.

Refer also to Material Safety Data Sheet.

FOR INDUSTRIAL USE ONLY.

LIMITED WARRANTY: All statements, technical information and recommendations contained herein are based on tests the manufacturer believes to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, express or implied:

Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective at the time the sealed container is first opened, and in no event beyond the shelf life date printed on the label. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, use shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.

All data, statements and recommendations made herein are based upon information manufacturer believes to be reliable, but are made without any representation or guaranty or warranty of accuracy and are made with reservation of all patent rights. All products are sold on the condition that the user will evaluate them, as well as manufacturer's recommendation, to determine their suitability for user's own purpose before adoption. Statements regarding the use of the products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations.

Rev. 10/05