



info@cficoatings.com +1-877-723-0919 www.cficoatings.com +1-215-723-0919

319 Township Line Rd. Souderton, PA 18964

# **U-Series**

U-498

#### DESCRIPTION

Two-component high build, high solids polyamidecured novolac epoxy finish coating.

## **COLORS**

Available in standard full gloss colors. Special colors and gloss can be matched upon request.

#### **PACKAGING**

Available in one-gal and five-gal kits, premeasured for easy blending at the jobsite.

#### **FEATURES**

- Very surface tolerant; can be applied in damp environments.
- Economical coating with good abrasion and chemical resistance.
- Best used as a topcoat for U-Series primers

#### **USES**

U-498 can be used on submerged or non-submerged metal and concrete surfaces. This coating has good abrasion and chemical resistance properties making it an excellent all-purpose general industrial coating.

#### **SURFACE PREPARATION**

Previously Painted or Rusted Surfaces – All previously coated surfaces in good condition do NOT need to be stripped. However, these surfaces should be roughened to help assure adhesion.

Bare surfaces should be cleaned and primed with CFI U-Series primers; U-104, U-109, U-497, U-499.

Submerged Surfaces – Concrete should be etched or profiled and primed with U-499.

All surfaces should be free of grease, oil, dirt, or other contaminants.

Technical Data	
Volume Solids:	60% (Will vary slightly)
Weight Solids:	73% (Depending on color)
Dry Film Thickness,	
Min.:	3 mils DFT
Max.:	5 mils DFT
Coverage @ 4 mils DFT:	250 sq. ft. / gal.
Dry Time,	To Touch – 2 to 4 hrs.
(70°F, 50% R.H.):	Full Physical Properties – 2 to 3 days
(/U F, JUM N.H.):	Full Resistance Properties – 7 days
Pot Life (70°F, 50% R.H.):	6 hrs.
Min. Application Temp.:	50°F
Service Temp. Range:	0°F to 250°F
Method of Application:	Brush, roller, or spray
Thinners:	CFI 735 Thinner for Brushing
	CFI 711 Thinner for Spraying
Cleaner:	CFI 704 Cleaner
Induction Time:	None
Mix Ratio:	4:1 by volume





info@cficoatings.com +1-877-723-0919 www.cficoatings.com +1-215-723-0919

319 Township Line Rd. Souderton, PA 18964

# **U-Series**

U-498

### **APPLICATION**

Thoroughly mix Part A, then add Part B; then mechanically mix for a minimum of 3 minutes.

Apply by brush, roller, or spray. Do not apply when the temperature of the substrate is below 50°F.

Maintain a wet film thickness of between 5 and 8 mils. Thicker film builds will cause a considerably longer tackfree dry time.

#### **PRECAUTIONS**

Contains aromatic hydrocarbons and glycol ethers.

HARMFUL OR FATAL IF SWALLOWED.

**COMBUSTIBLE** 

Vapor Harmful, Eye Irritant. If swallowed, do not induce vomiting. Call physician immediately. Avoid prolonged contact with skin, do not breathe vapor or spray mist. In case of contact with eyes, flush repeatedly with water and contact physician.

Keep away from heat, sparks and open flames. Prohibit smoking. Use non-sparking equipment. Use with adequate ventilation. In confined areas, use adequate forced ventilation during application and drying.

In areas where there is a minimum of air movement, a fresh air mask (such as #W-92 manufactured by 3M Co.) should be used.

READ THE SAFETY DATA SHEET PRIOR TO USE.